



Non-woven geotextile: RM-200

Product – Polypropylene Class II

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
Weight	ASTM D5261	g/m ² (oz./yd ²)	203 (6.0)
Grab Tensile Strength	ASTM D4632	lbs (N)	160 (712)
Grab Tensile Elongation	ASTM D4632	%	50
Trapezoid Tear Strength	ASTM D4533	lbs (N)	60 (267)
CBR Puncture Strength	ASTM D6241	lbs (N)	410 (1824)
			Maximum Opening Size
Apparent Opening Size(AOS)	ASTM D 4751	mm	0.132
			Minimum Roll Value
Permittivity	ASTM D4491	Sec ⁻¹	1.5
Flow Rate	ASTM D 4491	gal./min/ft ² (l/min/m ²)	120 (4882)
			Minimum Test Value
UV Resisitance (at 500 hours)	ASTM D4355	% strength retained	70

Disclaimer: All values are MARV except where specified. This information is provided for reference purposes only and is not intended as a warranty or guarantee. Randall Manufacturing Inc. assumes no liability in connection with no control over the use, the installation and/or the improper use of the geotextile described in this document.

Randall Manufacturing Inc. All Rights Reserved.