



RM130 Nonwoven Geotextile

Product – Needlepunch 3oz Civil Geotextile

Fiber Type – High Tenacity Synthetic Staple Fiber

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
Grab Tensile Strength	ASTM D4632	N	401
Grab Tensile Elongation	ASTM D4632	%	>50
Trapezoid Tear Strength	ASTM D4533	N	178
CBR Puncture Strength	ASTM D6241	N	1178
Hydraulic Properties			
Apparent Opening Size (AOS) *	ASTM D 4751	mm	0.30
Permittivity	ASTM D4491	Sec-1	2.0
Flow Rate	ASTM D 4491	L/min/m ²	6095
Filtration Opening Size (FOS)	CAN148.1 No.1	µm	90-200
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70

Disclaimer: All values are MARV except where specified (*). Randall Manufacturing Inc. assumes no liability in connection with the installation and/or the improper use of the geotextile described in this document.

Randall Manufacturing Inc. All Rights Reserved.